



West Yorkshire Materials Testing Service

West Yorkshire Joint Services

West Yorkshire Materials Testing Service
PO Box 5, Nepshaw lane South, Morley,
Leeds LS27 0QP
Tel: 0113 253 0241 Fax: 0113 252 7029
Head of Laboratory: G. Briggs C. Text ATI

Client: Dartex Coatings Ltd
Acton Close
Long Eaton
Nottingham
Nottinghamshire
NG101FZ

Entry No: 60840

Date received: 25/06/2013

Client's Description: Sample of fabric PER200 Batch 305-509 Shade blue on scour Polyurethane coated on a weft knit polyamide fabric

TEST REPORT

Test Required: Flammability BS 7175 ignition source 5
Pre-treatment: None
Conditioning: A minimum of 72 hours at indoor ambient and then 24 hours at 65 +/- 5% Relative Humidity, 20 +/- 5°C
Method of Test: BS 7175: 1989 (2008) Section 3
Date of Test: 04/07/2013

The following test results relate only to the ignitibility of the combination of materials under the particular conditions of test: they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Ignition Source	Positions	Observations	Result
5 (wood crib)	(i) On Top (ii) Below Overhang	Flaming ceased within the specified ten minute period after ignition of the crib and no progressive smouldering occurred.	PASS

-----End of Page-----

CONFIDENTIAL
Property of
Dartex Coatings

This is hereby certified to be a correct return of the tests made of the items referred to herein.

Geoff Briggs C.Text., A.T.I.
Head of laboratory
10th July 2013



- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.





West Yorkshire Materials Testing Service

West Yorkshire Joint Services

West Yorkshire Materials Testing Service
PO Box 5, Nepshaw lane South, Morley,
Leeds LS27 0QP
Tel: 0113 253 0241 Fax: 0113 252 7029
Head of Laboratory: G. Briggs C. Text ATI

Client: Dartex Coatings Ltd
Acton Close
Long Eaton
Nottingham
Nottinghamshire
NG101FZ

Entry No: 60840

During the tests the following data was recorded: -

Ignition Source: - 5 (wood crib)

On Top

Below

	On Top	Below
Time of ignition (sec)	8	10
Time to extinction of flaming (sec)	375	461
Time to extinction of smoke (sec)	513	629
Damage in length (mm)	188	231
Damage in width (mm)	196	258
Melting (Yes or No)	Yes	Yes
Dripping (Yes or No)	No	No
Charring (Yes or No)	Yes	Yes

-----End of Document-----

CONFIDENTIAL
Property of
Dartex Coatings

This is hereby certified to be a correct return of the tests made of the items referred to herein.

Geoff Briggs C.Text., A.T.I.
Head of laboratory
10th July 2013



- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

