



TEST REPORT

Technical Report: (5114)345-0125

Page 1 of 5
December 17, 2014



Bureau Veritas Consumer Products Services, Inc.
100 Northpointe Parkway
Buffalo, New York 14228
Telephone: (716) 505-3300 Fax: (716) 505-3301
website: www.bureauveritas.com/cps

This report is governed by, and incorporates by reference, the Conditions of Testing as posted at the date of issuance of this report at <http://www.bureauveritas.com/cps> and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. You have 60 days from date of issuance of this report to notify us of any material error or omission caused by our negligence; provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.



TEST REPORT

TO : EASTEX PRODUCTS
 275 CENTRE ST.
 HOLBROOK MA, 02343

ATTN : DEE PIERCE

LAB NO.: (5114)345-0125
FORM NO.: /
DATE IN: December 11, 2014
DATE OUT: December 17, 2014
NO. OF WORKING DAYS: 4
PAGE 2 OF 4

OVERALL RATING

PASS	X
FAIL	_____
DATA	_____

Vendor:	/	Agent:	/
Fabric Supplier/Mill:	/	Factory/Manufacturer:	/
P.O. No.:	/	Style No.:	/
Sample Description:	SW 6000 / TEK STRETCH 4	Style Description:	/
Color:	/	Country of Origin:	TAIWAN
Claimed Fabric Weight:	/	Claimed Fabric Count:	/
Yarn Size:	/	Submitted Size:	/
Size Range:	/	FPU No.:	/
GPU No.:	/	End Use:	/

Product Category	FABRIC
Test Requested	CA1117 2013
Previous Report No.	/

Submitted Fiber Content	/
Actual Fiber Content	/
Suggested Fiber Content	/
Submitted Care Instruction(s)	/
Client Expected Care Instruction	/
Suggested Care Instruction(s)	/



BUREAU
VERITAS

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
CALIFORNIA TECHNICAL BULLETIN 117-2013	X			

Technical Questions:

Phone: 716-505-3410 softlinetechnicalsupportMail@us.bureauveritas.com

Bureau Veritas
Consumer Products Services, Inc.

Jackie Graves
Manager - Softlines



TEST PROPERTY

TEST RESULTS

REQUIREMENTS

The sample(s) MEET the following requirements:

- The flammability requirements of California Technical Bulletin 117-2013, Section 1 – Cover Fabric.

TEST RESULT

Flammability of cover fabric test

Test Method: California Technical Bulletin CA TB 117-2013 Section I

Tested Item(s): BLUE

RESULT FOR INITIAL TEST:						
Fabric	Obvious Ignition/ Open flaming	Sustained Smoldering after 45min	Re-Light	No. of Re-Lights	Vertical Char Length/ in	Individual Rating
1	N	N	N	---	0.4	Meets
2	N	N	N	---	0.5	Meets
3	N	N	N	---	0.3	Meets
Overall Rating						PASS

<p>CRITERIA:</p> <ol style="list-style-type: none"> 1. A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs: <ol style="list-style-type: none"> a) The mock-up test specimen continues to smolder after the 45 minute test duration; b) A vertical char length (measured as specified in step 11.9 of ASTM E1353-08a) of more than 1.8 inches (51 mm) develops on the cover fabric. c) The mock-up test specimen transitions to open flaming. 2. The cover fabric material passes the test if three initial mock-up specimens pass the test, i.e. the cigarettes burn to their full length. 3. If more than one specimen fails, the cover fabric material fails the test. 4. If any one of the three initial specimens fails, repeat the test on additional three specimens. 5. If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test.
--

Y=Yes N=No M=Meets NM=Does Not Meet
 DATA = Record data only NA = Not Applicable NR= Not requested NT=Not Tested



The sample(s) MEET the following requirements:

- The flammability requirements of California Technical Bulletin 117-2013, Section 1 – Cover Fabric.

TEST RESULT

Flammability of cover fabric test

Test Method: California Technical Bulletin CA TB 117-2013 Section I

Tested Item(s): GREY

RESULT FOR INITIAL TEST:						
Fabric	Obvious Ignition/ Open flaming	Sustained Smoldering after 45min	Re-Light	No. of Re-Lights	Vertical Char Length/ in	Individual Rating
1	N	N	Y	2	0.0	Meets
2	N	N	Y	2	0.0	Meets
3	N	N	Y	2	0.0	Meets
Overall Rating						PASS

CRITERIA:

1. A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:
 - a) The mock-up test specimen continues to smolder after the 45 minute test duration;
 - b) A vertical char length (measured as specified in step 11.9 of ASTM E1353-08a) of more than 1.8 inches (51 mm) develops on the cover fabric.
 - c) The mock-up test specimen transitions to open flaming.
6. The cover fabric material passes the test if three initial mock-up specimens pass the test, i.e. the cigarettes burn to their full length.
7. If more than one specimen fails, the cover fabric material fails the test.
8. If any one of the three initial specimens fails, repeat the test on additional three specimens.
9. If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test.

Y=Yes

DATA = Record data only

N=No

NA = Not Applicable

M=Meets

NR= Not requested

NM=Does Not Meet

NT=Not Tested